



S.E.A.
OLYMPUS
Marketing, Inc.

www.olympus.com.ph

PolyKlear®
FIBERGLASS + RESIN

PolyKlear®
FIBERGLASS + RESIN

PolyKlear®
FIBERGLASS + RESIN

MATERIAL SAFETY DATA SHEET

M GLASS FIBER E-CHOPPED STRANDS (3MM, 6MM)

PolyKlear®
FIBERGLASS + RESIN

Section 1: PRODUCT IDENTIFICATION

C.A.S. NUMBER : 65999-17-3

COMMON NAME : ACM GLASS FIBER E-CHOPPED STRANDS (3MM, 6MM)

PRIMARY USAGE : FOR REINFORCEMENT

PolyKlear®
FIBERGLASS + RESIN

PolyKlear®
FIBERGLASS + RESIN

PolyKlear®
FIBERGLASS + RESIN

Section 2: INGREDIENTS NOMINAL VALUES

E-GLASS (ALKALI CONTENT) : Less than 0.80 %

Combustible : 2.10-6.30 %

PolyKlear®
FIBERGLASS + RESIN

PolyKlear®
FIBERGLASS + RESIN

PolyKlear®
FIBERGLASS + RESIN

Section 3: PHYSICAL DATA

BOILING POINT : N.A.

%VOLATILE BY VOLUME : NONE

MELT POINT : N.A.

VAPOR DENSITY : N.A.

%SOLUBILITY (H2O) : NEGLIGIBLE

SPECIFIC GRAVITY-FILAMENT : 2.3G/CM3

VAPOR PRESSURE : N.A.

APPEARANCE : white, clean

ODOR : NONE

PolyKlear®
FIBERGLASS + RESIN

PolyKlear®
FIBERGLASS + RESIN

PolyKlear®
FIBERGLASS + RESIN

Section 4: FIRE AND EXPLOSION HAZARD DATA

FLASH POINT AND METHOD : N.A.

FLAMMABLE LIMITS LET : N.A.

FLAMMABLE LIMITS VEL : N.A.

EXTINGUISHING MEDIA : USE WATER AND FOAM ONLY THE
PACKAGING BURNS

PolyKlear®
FIBERGLASS + RESIN

PolyKlear®
FIBERGLASS + RESIN

PolyKlear®
FIBERGLASS + RESIN

SPECIAL FIRE FIGHTING PROCEDURES : N.A.

UNUSUAL FIRE AND EXPLOSION HAZARD : N.A.

LUZON:

REGIONAL OFFICE
TAGUIG
1st Avenue, Sta. Maria Industrial Subd,
Bagumbayan, Taguig City
Tel. #: (02) 506-8519 ; 837-0710
837-0708

VISAYAS:

HEADQUARTERS
CEBU
2F SEA Olympus Building, AC Cortes Ave.
Trunkline #: (032) 421-7777
Tel. #: (032) 346-7137 ; 421-7800 to 06
421-7817 to 18 ; 421-7823
Fax #: (032) 421-7789 ; 346-1817

MINDANAO:

REGIONAL OFFICE
DAVAO
Unit A16 J.King Warehouse Complex
Km.3 Maa Road, Davao City 8000
Telefax #: (082) 244-1206 ; 302-2711

inquiry@olympus.com.ph



s.e.a.
OLYMPUS
Marketing, Inc.

www.olympus.com.ph

Poly Klear
FIBERGLASS + RESIN

Section 5: HEALTH EFFECTS

HANDLING OF GLASS FILAMENTS MAY CAUSE TEMPORARY SKIN, EYE AND UPPER RESPIRATORY IRRITATION.

Section 6: EMERGENCY AND FIRST AID PROCEDURES

UPPER RESPIRATORY IRRITATION : REMOVE FROM EXPOSURE

SKIN CONTACT : CLEANSE WITH SOAP AND WARM WATER

EYE CONTACT : FLUSH WELL WITH RUNNING WATER FOR

10 MINUTES

Section 7: SPECIAL PROTECTION INFORMATION

USE GLASSES, GLOVES AND LOOSE FITTINGS TO AVOID TEMPORARY IRRITATION

Section 8: REACTIVITY

THIS IS A STABLE MATERIAL

Section 9: TRANSPORTATION AND DISPOSAL INFORMATION

GLASS FILAMENT PRODUCTS ARE NOT CONSIDERED AS DANGEROUS ACCORDING TO TRANSPORTATION REGULATIONS AND ARE THEREFORE SUBJECT TO NO SPECIAL PROCEDURE.

MAINTAIN IN ORIGINAL PACKAGING.

Section 10: SPILL LEAK AND DISPOSAL INFORMATION

SPILL AND LEAKS : N.A.

WASTE DISPOSAL : SCRAP MATERIAL SHOULD BE DISPOSED OF IN A SANITARY LANDFILL IN ACCORDANCE WITH LOCAL GOVERNMENT REGULATIONS

SEA Olympus Marketing, Inc. reserves the right to change the information given herein without prior notice. We believe this information to be reliable, but do not guarantee its applicability to the user's process or assume liability for occurrence arising out of its use. The user, by accepting products described herein agrees to be responsible for thoroughly testing any application before committing to production. ©20

Luzon:

REGIONAL OFFICE
TAGUIG
1st Avenue, Sta. Maria Industrial Subd,
Bagumbayan, Taguig City
Tel.#: (02) 506-8519 ; 837-0710
837-0708

VISAYAS:

HEADQUARTERS
CEBU
2F SEA Olympus Building, AC Cortes Ave.
Trunkline #: (032) 421-7777
Tel.#: (032) 346-7137 ; 421-7800 to 06
421-7817 to 18 ; 421-7823
Fax #: (032) 421-7789 ; 346-1817

Mindanao:

REGIONAL OFFICE
DAVAO
Unit A16 J.King Warehouse Complex
Km.3 Maa Road, Davao City 8000
Telefax #: (082) 244-1206 ; 302-2711

inquiry@olympus.com.ph



s.e.a.
OLYMPUS
Marketing, Inc.

www.olympus.com.ph

Poly Klear
FIBERGLASS + RESIN

Poly Klear
FIBERGLASS + RESIN

TECHNICAL DATA SHEET

MATERIAL NAME: ACM GLASS FIBER E-CHOPPED STRANDS (3MM , 6MM)

MATERIAL CODE: ECS

Alkali Resistant Chopped strand has excellent properties with alkali resistance, bundle-state, stiffness, and aging-proof. It is designed for ease of incorporation even at high dosage and remains integral during mixing. It is used in the manufacture of standard GRC components such as meter boxes or drainage channels, as well as in architectural applications such as decorative screen walling.

PROPERTIES

1. Good fluidity
2. Easy incorporation
3. Excellent bundle size
4. High integrity during mixing
5. High durability
6. Good wetting-out
7. Excellent flexibility

TECHNICAL CHARACTERISTICS

Product code	Filament Diameter (microns)	Chop Length (mm)	Loss on ignition (%)	Moisture (%)
ECS3MM	11	3	0.80±0.20	≤0.20
ECS6MM	11	6	0.80±0.20	≤0.20

PACKAGE

ECS is bundled into individual 1kg bulk bags. Polypropylene (PP) bags are used and can be placed in a pallet enough for about 36 bags.

STORAGE

Unless otherwise specified, it is recommended to store chopped strands in a cool, dry area. Temperature should not exceed 35°C (95°F) and the relative humidity should be kept below 75%. Chopped strands must remain in packaging material until just prior to their use. If these conditions are respected, the chopped strands should not undergo significant changes when stored for extended periods of time.

Poly Klear
FIBERGLASS + RESIN

LUZON:

REGIONAL OFFICE
TAGUIG
1st Avenue, Sta. Maria Industrial Subd,
Bagumbayan, Taguig City
Tel.#: (02) 506-8519 ; 837-0710
837-0708

Poly Klear
FIBERGLASS + RESIN

VISAYAS:

HEADQUARTERS
CEBU
2F SEA Olympus Building, AC Cortes Ave.
Trunkline #: (032) 421-7777
Tel.#: (032) 346-7137 ; 421-7800 to 06
421-7817 to 18 ; 421-7823
Fax #: (032) 421-7789 ; 346-1817

MINDANAO:

REGIONAL OFFICE
DAVAO
Unit A16 J.King Warehouse Complex
Km.3 Maa Road, Davao City 8000
Telefax #: (082) 244-1206 ; 302-2711

inquiry@olympus.com.ph