



# **Material Safety Data Sheet**

POLYKLEAR PP Honeycomb

Poly Klear



**Product Name: POLYKLEAR PP Honeycomb** 

**Chemical Product** 

|    | Single           |         | BERGLASS - RE     | 5171               |
|----|------------------|---------|-------------------|--------------------|
|    | Product/Mixed    | Mixed   |                   |                    |
| 3, | Product          | Product | Empirical Formula | CH2=CH - CH3       |
|    | Product Chemical |         |                   | r big Ma           |
| ĒΈ | Property RES     | N       | Polypropylene, Po | lyolefin elastomer |

### **Hazardous Effects**

|   |                      | 热           | BERGLASS + HE                | 51N                                  |      |
|---|----------------------|-------------|------------------------------|--------------------------------------|------|
|   | Risk                 | Non-toxic   | Nocuity                      | innocuity                            |      |
|   | oly Kleai            | No toxicity | or irritant action on respir | atory organs under normal industrial | ł    |
| P | Health Effect        | 24          | usa                          | ge FIBERGLASS + 1                    | 18.E |
|   | Environmental Effect |             | Non-                         | toxic                                |      |

### Police (4) **First Aid Measurement**

|      | Y 7/4         | No first aid is usually required. In hot product - immediately wash with cold  |
|------|---------------|--|
| H    | Skin          | water  |
| FIBE | RGLASS - RESI | Do not use hand wipe, lest stimulate or damage the cornea, irrigate with flowing water; if there are any abnormalities, go to the hospital for check-up. |
|      | Inhalation    | From the scene, move to a place having fresh air once encounter difficulty in breathing- an oxygen treatment.  |
|      | Ingestion     | No acute poisoning; spit out immediately once ingested. Refer to the hospital for check-up.  |

### **Fire Protection**

| AND THE RESIDENCE OF THE PARTY |   |  |  |
|---|---|--|--|
| Environmental Effect  | Flammable Gas Heating decomposition                             |  |  |
| Extinguishing   |   |  |  |
| Method  | Remove from the fire to empty the container as soon as possible |  |  |
| Extinguishing Agent   | Fog water/Foam Powder/Sandy soil/Carbon dioxide                 |  |  |





#### LUZON:

REGIONAL OFFICE Tast Avenue, Sta. Maria Industrial Subd, Bagumbayan, Taguig City Tel.#: (02) 506-8519; 837-0710 837-0708



HEADQUARTERS

HEADQUAKTERS
CEBU
2F SEA Olympus Building, AC Cortes Ave.
Trunkline #: (032) 421-7777
Tel.#: (032) 346-7137; 421-7800 to 06
421-7817 to 18; 421-7823
Fax #: (032) 421-7789; 346-1817

### MINDANAO:

REGIONAL OFFICE Unit A16 J.King Warehouse Complex Km.3 Maa Road, Davao City 8000 Telefax #: (082) 244-1206; 302-2711





| Usage           | widely use d in tuck body, floor, door, boat exterior, duck, curtain walls  |  |
|-----------------|---|--|
| ERGLASS / RESIN | Store in a cool, ventilated warehouse. Away from fire and heat source. Should be stored apart with antioxidant. Equipped with |  |
| Storage         | corresponding varieties and fire equipment.   |  |

| Respiratory System Care |                      | Not necessary as usual |
|-------------------------|----------------------|------------------------|
| Eye Care                |                      | No special requirement |
|                         | Hand care            | Wear safety gloves     |
| Body care               |                      | Wear uniform           |
| E                       | EERGLAS others? ESIN | No smoking, keep clean |

## **Physical Property**

| Material Status | Solid      | Density    | 80Kg/m3 |
|-----------------|------------|------------|---------|
| Melting Point   | 240-250 °C | SS + HESTN |         |

### **Dangerous Situation**

| ENGLISS I RESIDEA |     |                    |     |  |
|-------------------|-----|--------------------|-----|--|
| Incendivity       | Yes | Flammability       | Yes |  |
| Acidification     | No  | Chemical Stability | Yes |  |
| Dust Explosion    | No  | Stability          | No  |  |

### **Toxicological Information**

| Acute Toxicity | LD 50: No Data<br>LC50: No data | Sub-acute and chronic | FIBE No LASS |
|----------------|---------------------------------|-----------------------|--------------|
| Acrimony       | No                              | Allergenic            | No           |
| Teratogenicity | No                              | Carcinogenicity       | No           |

## **Ecological Information**

| Ecological Info  | Recycled FILLEH GILA 8.3 H |
|------------------|----------------------------|
| Lcological IIIIo | riccyclcu                  |

### **Disposal Consideration**

|                        | All waste must be handled in accordance with Note on the use and |
|------------------------|--|
| Disposal Consideration | storage; recycle or incineration disposal                        |

### Transportation

#### LUZON:

REGIONAL OFFICE Takender Sta. Maria Industrial Subd, Bagumbayan, Taguig City
Tel.#: (02) 506-8519; 837-0710
837-0708

# VISAYAS:

HEADQUARTERS

CEBU
2F SEA Olympus Building, AC Cortes Ave.
Trunkline #: (032) 421-7777
Tel.#: (032) 346-7137; 421-7800 to 06
421-7817 to 18; 421-7823
Fax #: (032) 421-7789; 346-1817

### MINDANAO:

REGIONAL OFFICE DAYAO Unit A16 J.King Warehouse Complex Km.3 Maa Road, Davao City 8000 Telefax #: (082) 244-1206; 302-2711





Information

**Transportation Information** 

be handled in accordance with the Note on the usage and storage

# **Regulatory Information**

PP Honeycomb

No regulations applicable

Polypropylene (CAS:9003-07-0) is found on the following regulation lists DSL, WHMIS, IARC, TEELs, PELs, TSCA

















The data and information contained in this Material Safety Data Sheet is provided to the best of our knowledge and ability on existing hazards, properties and handling of this product as recommended. It is recommended that the user tests the product according to its purpose. The user is responsible for the proper, safe and lawful use of this product. The information contained in this MSDS is subject to change without further notice. © 20

#### LUZON:

REGIONAL OFFICE 1st Avenue, Sta. Maria Industrial Subd, Bagumbayan, Taguig City Tel.#: (02) 506-8519 ; 837-0710 837-0708

### VISAYAS:

**HEADQUARTERS** TEADQUARTERS
CEBU
2F SEA Olympus Building, AC Cortes Ave.
Trunkline #: (032) 421-7777
Tel.#: (032) 346-7137; 421-7800 to 06
421-7817 to 18; 421-7823
Fax #: (032) 421-7789; 346-1817

### MINDANAO:

REGIONAL OFFICE Unit A16 J.King Warehouse Complex Km.3 Maa Road, Davao City 8000 Telefax #: (082) 244-1206; 302-271:





# TECHNICAL DATA SHEET POLYKLEAR PP HONEYCOMB

### A. DESCRIPTION

Polyklear PP8-80T30 PLASTIC HONEYCOMB is lightweight and high compressive strength, PP8-80T30 PLASTIC HONEYCOMB, has been widely used as the core material for truck body.

## **B. APPLICATIONS**

As core material laminated with other panels, can be used for truck side wall, floor, doors, curtain, walls in exterior design, bed board, bathroom, etc. Light with high compressive strength, easy to assemble, waterproof, recyclable, easy repair and long service life.

High compressive strength to weight ratio Energy absorption Sound insulation Heat insulation Anti-water, corrosion resistance

Boned with face panel-FRP, have good performance in corrosion resistance to oil, salt and other chemicals.

#### **D. PROPERTIES**

| Proper | ties | of PP |
|--------|------|-------|
| Honeyo | om   | h·    |

|   | Honeycomb:            |         |                 |               |
|---|-----------------------|---------|-----------------|---------------|
| P |                       | unit    | value           |               |
|   |                       | mm      | 8               |               |
|   | diameter              |         |                 |               |
|   |                       | Kg/m3   | 80              |               |
|   | density               |         |                 |               |
|   |                       | Mpa     | 1.3             | GB/T8813-2008 |
|   | compressive strength  |         |                 |               |
|   |                       | Mpa     | 70              | GB/T8813-2008 |
|   | compressive modulus   |         |                 |               |
|   |                       | Mpa     | 0.5             | GB/T1455-2005 |
|   | shear strength        |         |                 |               |
|   |                       |         | <b>-</b> 40∼+80 |               |
|   | effective temperature |         |                 |               |
| _ |                       | W/mk,10 | 0.102           |               |
|   | thermal conductivity  | ŕ       |                 |               |

Note: base on testing data of 30mm honeycomb

#### LUZON:

REGIONAL OFFICE 1st Avenue, Sta. Maria Industrial Subd, Bagumbayan, Taguig City Tel.#: (02) 506-8519 ; 837-0710 837-0708

# VISAYAS:

HEADQUARTERS MEADQUARTERS
CEBU
2F SEA Olympus Building, AC Cortes Ave.
Trunkline #: (032) 421-7777
Tel.#: (032) 346-7137; 421-7800 to 06
421-7817 to 18; 421-7823
Fax #: (032) 421-7789; 346-1817

### MINDANAO:

REGIONAL OFFICE Unit A16 J.King Warehouse Complex Km.3 Maa Road, Davao City 8000 Telefax #: (082) 244-1206; 302-271:





Marketing, Inc.
www.olympus.com.ph

Poly Klear

E. STORAGE

Polyklear PP8-80T30 PLASTIC HONEYCOMB should be stored in a cool, ventilated warehouse. Away from fire and heat source and should be stored apart with antioxidant. Equipped with corresponding varieties and fire equipment

### F. PACKING

**Carton Packaging** 

Poly Klear

Poly Klear,

SEA Olympus Marketing Inc. reserves the right to change the information given herein without prior notice. The company within the scope of knowledge, the file information accurate reliable, however, due to the actual use is not in my company's products are manageable, users have the responsibility to judge for themselves in the specific application of all risk we do not promise, the result of the use and is not liable for relevant recommendations and Suggestions are recommended in this article content using all the information, not be construed to suggest infringement of any patent or applicable laws provide sample does not contain any warnings, meaning and implication. ©20

Poly Klear

Poly Klear









#### LUZON:

REGIONAL OFFICE TAGUIG 1st Avenue, Sta. Maria Industrial Subd, Bagumbayan, Taguig City Tel.#: (02) 506-8519 ; 837-0710 837-0708 VISAYAS:

HEADQUARTERS
CEBU
2F SEA Olympus Building, AC Cortes Ave.
Trunkline #: (032) 421-7777
Tel.#: (032) 346-7137; 421-7800 to 06
421-7817 to 18; 421-7823
Fax #: (032) 421-7789; 346-1817

MINDANAO:

REGIONAL OFFICE DAVAO Unit A16 J.King Warehouse Complex Km.3 Maa Road, Davao City 8000 Telefax #: (082) 244-1206; 302-271