



MATERIAL SAFETY DATA SHEET

POLYKLEAR R99-S205-03 PREMIX THIXOTROPED (BQTN-O)

Section 1: Product Identification

Product Name : POLYKLEAR R99-S205-03 PREMIX THIXOTROPED (BQTN-O)

Grade : Orthophthalic Laminating Resin

DOT Shipping Name : Resin solution DOT Hazard Class : Flammable Liquid

Section 2: Hazards Identification

GHS Classification:

FLAMMABLE LIQUIDS, Category 3

ACUTE TOXICITY - INHALATION, Category 4

SKIN CORROSION/IRRITATION, Category 2

SPECIFIC TARGET ORGAN SYSTEMIC TOXICITY (SINGLE EXPOSURE), Category 3

Respiratory tract irritation

SERIOUS EYE DAMAGA/IRRITATION, Category 2

ASPIRATION HAZARD, Category 1

SPECIFIC TARGET ORGAN SYSTEMIC TOXICITY (REPEATED EXPOSURE),

Category 1

Auditory system and Central nervous system (CNS)

AQUATIC TOXICITY (ACUTE), Category 2

GHS label elements:

Symbol(s)







LUZON:

REGIONAL OFFICE 1st Avenue, Sta. Maria Industrial Subd. Bagumbayan, Taguig City Tel.#: (02) 506-8519; 837-0710

VISAYAS:


HEADQUARTERS

ZF SEA Olympus Building, AC Cortes Ave. Trunkline #: (032) 421-7777 Tel.#: (032) 346-7137; 421-7800 to 06 421-7817 to 18; 421-7823 Fax #: (032) 421-7789; 346-1817

MINDANAO:

REGIONAL OFFICE Unit A16 J.King Warehouse Complex Km.3 Maa Road, Davao City 8000 Telefax #: (082) 244-1206; 302-2711









: PHYSICAL HAZARDS



Polu Ke

: H226: Flammable liquid and vapor.

: HEALTH HAZARDS:

: H304: May be fatal if swallowed and enters airways.

: H332: Harmful if inhaled.

: H315: Causes skin irritation.

: H319: Causes serious eye irritation.


: H355: May cause respiratory irritation.

: H372: Causes damage to organs through prolonged or

repeated exposure

: ENVIRONMENT HAZARDS:

: H401: Toxic to aquatic life.



Prevention

P210: Keep away from heat/sparks/open flames/hot surfaces. – No smoking.

P233: Keep container tightly closed.

P243: Take precautionary measures against static discharged.

P260: Do not breathe dust/fume/gas/mist/vapours/spray.

P264: Wash hands thoroughly after handling.

P271: Use only outdoors or in a well-ventilated area.

P273: Avoid release to the environment.

P280: Wear protective gloves/protective clothing/eye protection/face protection

P304+P340: IF INHALED: Remove to fresh air and keep at rest in a position comfortable for breathing.

P303+P361+P353: IF ON SKIN (or hair): Remove/take off immediately all contaminated clothing. Rinse skin with water/shower.

P332+P313: If skin irritation occurs: Get medical advice/attention.

P305+P351+P338: IF IN EYES: Rinse cautiously with water for several minutes. Remove contact lenses, if present and easy to do. Continue rinsing.

P337+P313: If eye irritation persist: Get medical advice/attention.

P301+P330+P331: IF SWALLOWED: Rinse mouth. Do NOT

induce vomitting.

 MINDANAO:

REGIONAL OFFICE DAVAO Unit A16 J.King Warehouse Complex Km.3 Maa Road, Davao City 8000 Telefax #: (082) 244-1206; 302-2711

inquiry@olympus.com.ph

Response





LUZON:

REGIONAL OFFICE TAGUIG 1st Avenue, Sta. Maria Industrial Subd, Bagumbayan, Taguig City Tel.#: (02) 506-8519; 837-0710 837-0708



Disposal



www.olympus.com.ph

P370+P378: In case of fire: Use appropriate media for extinction.

P403+P233: Store in a well-ventilated place. Keep container tightly closed.

P235: Keep cool.

P501: Dispose of contents and container to appropriate waste

site or reclaimer in accordance with local and national

Other Hazards Vapours are heavier than air. Vapours may travel across the which do not result ground and reach remote ignition sources causing a flashback in classification fire danger.

May form flammable/explosive vapour-air mixture.

Maintain dissolved oxygen and inhibitor at proper levels to

prevent runaway polymerisation.

Repeated exposure may cause skin dryness or cracking.

Aggravated Medical Pre-existing medical conditions of the following organ(s) system(s) may be aggravated by exposure to this material:

Central nervous system (CNS), auditory system, and

Respiratory system

Section 3: Information on Hazardous Components

Component	CAS No.	Percentage	Threshold Limit
			Value
Styrene	100-42-5	38%	50ppm
Polyester		62%	

Section 4: First Aid Measures

Ingestion: Harmful if swallowed. Single dose oral toxicity is low. Do not induce vomiting. Aspiration of material into the lungs could cause pneumonitis which can be fatal. Give milk or water. Seek medical attention.

Inhalation of Vapour: Harmful. Effects may include headache, nausea, fatigue, central nervous system depression, pulmonary oedema. May be irritating to nose, throat and respiratory tract. Move victim to fresh air. Apply artificial respiration or give oxygen if necessary. Seek medical attention.

Eye Contact: Irritant. Flush with copious amounts of water - lift eyelids repeatedly. Seek medical attention.

LUZON:

REGIONAL OFFICE TAGUIG 1st Avenue, Sta. Maria Industrial Subd. Bagumbayan, Taguig City Tel.#: (02) 506-8519 ; 837-0710

VISAYAS:

HEADQUARTERS

ZF SEA Olympus Building, AC Cortes Ave. Trunkline #: (032) 421-7777 Tel.#: (032) 346-7137 ; 421-7800 to 06 421-7817 to 18 ; 421-7823 Fax #: (032) 421-7789 ; 346-1817

MINDANAO:

REGIONAL OFFICE Unit A16 J.King Warehouse Complex Km.3 Maa Road, Davao City 8000 Telefax #: (082) 244-1206 ; 302-2711





Skin Contact: Irritant. Wash thoroughly with soap and water. Remove contaminated clothing and launder before re-use. Seek medical advice if irritation persists. Advice to Doctor: Treat symptomatically.

Section 5: Firefighting Measures

Flammable Limits: LEL 1.1% Flammable Liquid: 31°C UEL 6.1%

Flash Point: 31 °C Hazchem Code: 3[Y]

(Setaflash)

Extinguishing Media: Foam, Carbon Dioxide, Dry Powder, Water Fog **Unusual Fire and Explosion Hazards:**

Styrene will polymerise at elevated temperatures. If this occurs in a closed container, there is a risk of violent rupture.

Special Firefighting Procedures:

Fight like a fuel-oil fire. Water used in fire-fighting should not be allowed to enter drainage system or contaminate soil.

Section 6: Accidental Release Measures

Steps to be taken if the material is released or spilled:

Eliminate all sources of ignition (flames, hot surfaces, and electrical, static or frictional sparks). Ventilate area.

Dyke area of spill and pump material into drums for use or disposal. Absorb remainder on sand or perlite and place the saturated absorbent into closed containers for disposal. Prevent contamination of storm-water drains.

Waste disposal method. Destroy by liquid incineration with off-gas scrubber.

Contaminated absorbent to be incinerated or deposited in secure landfill in accordance with appropriate regulations.

Liquid material mixed with peroxide initiators should be allowed to gel before disposal as solid waste in accordance with appropriate regulations.

Section 7: Handling and Storage

- a) Avoid inhalation of vapour and contact with skin, eyes and clothing. Launder contaminated clothing before re-use.
- b) Wash hands thoroughly before eating.
- c) Ground (earth) all connections and containers when using above flash point.
- d) Store in a bunded area or approved flammable goods store away from direct heat (ideally below 27° C to prevent spoilage). Keep containers closed when not in use. Open drums slowly in case of internal pressure.

LUZON:

REGIONAL OFFICE 1st Avenue, Sta. Maria Industrial Subd. Bagumbayan, Taguig City Tel.#: (02) 506-8519 ; 837-0710

VISAYAS:

HEADQUARTERS ZF SEA Olympus Building, AC Cortes Ave. Trunkline #: (032) 421-7777 Tel.#: (032) 346-7137; 421-7800 to 06 421-7817 to 18; 421-7823 Fax #: (032) 421-7789; 346-1817

MINDANAO:

REGIONAL OFFICE Unit A16 J.King Warehouse Complex Km.3 Maa Road, Davao City 8000 Telefax #: (082) 244-1206 ; 302-2711





- e) Isolate from all potential sources of ignition including flames and electrical sparks.
- Store separate from oxidizing materials, peroxides and metal salts.

Section 8: Exposure Control/Personal Protection

Workplace Exposure Limit:

Styrene 50ppm

Use general dilution or local exhaust ventilation to maintain vapour concentration below WES level. If concentrations exceed exposure limit use organic vapour canister mask or approved air-line mask.

Skin Protection: Wear overalls or other work clothing providing arm and leg cover. Use protective gloves (PVC).

Eye Protection: Safety goggles or splash mask.

Section 9: Physical and Chemical Properties

Physical State : Liquid

: Clear, cloudy or coloured viscous liquid Appearance

Boiling Point (760mm HG) : 145 °C (Styrene)

: 1.1 - 1.7Specific Gravity

% Volatiles by Volume : 35.0%

Solubility in H20 : Insoluble

Fire and Explosion hazard

Flash Point :31 °C

: LEL 1.1% Flammable Limits

UEL 6.1%

Flammable limits of volatiles compound

Volatiles Styrene : 25 – 55 w/w

Section 11: Toxicological Information

When used under properly controlled conditions, within workplace exposure limits and with adequate protective equipment, no adverse health effects are to be expected.

Acute effects of over exposure.

If Swallowed: Harmful by ingestion. Possible irritation of mucous membranes, nausea, vomiting and gastric disturbance. Possible depression of central nervous system. Aspiration into lungs could cause pneumonitis which may damage lungs or may be fatal.

Eye Contact: Mild to moderate irritation. Reddening may occur if exposure is prolonged.

LUZON:

REGIONAL OFFICE 1st Avenue, Sta. Maria Industrial Subd. Bagumbayan, Taguig City Tel.#: (02) 506-8519 ; 837-0710

VISAYAS:

HEADQUARTERS

CEBU 2F SEA Olympus Building, AC Cortes Ave. Trunkline #: (032) 421-7777 Tel.#: (032) 346-7137; 421-7800 to 06 421-7817 to 18; 421-7823 Fax #: (032) 421-7789; 346-1817

MINDANAO:

REGIONAL OFFICE Unit A16 J.King Warehouse Complex Km.3 Maa Road, Davao City 8000 Felefax #: (082) 244-1206 ; 302-2711





Skin Contact: Irritant. May cause itching and redness of skin.

Inhalation of Vapour: May cause headaches, nausea, irritation of the respiratory tract and depression of the central nervous system.

Chronic effects of over exposure.

Mild dermatitis may result from prolonged or repeated skin contact. Styrene can be absorbed through the skin. Excessive exposure to the liquid material or vapour may affect the central nervous system, the liver, kidneys and respiratory system.

Section 12: Ecological Information

Prevent these products from entering storm-water drains sewers or waterways.

Styrene is the major contaminant hazard in these formulations and it will undergo slow (but near complete) biodegradation in contact with soil. Styrene vapour degrades rapidly in the atmosphere.

Styrene floats on water and will vaporise and biodegrade.

Section 13: Disposal Considerations

Waste Disposal: Small quantities of these products may be mixed with appropriate amounts of polymerisation initiators and allowed to solidify before disposal as solid waste.

Recover or recycle if possible.

This material and its container must be disposed of as hazardous waste.

Any disposal must comply with applicable local and national government regulations. Ensure that these materials do not enter drains, sewers or waterways.

Section 14: Transport Information

UN 1866 Identification number

Resin Solution, Flammable Proper shipping name

Class / Division

Packing group 111

Hazchem Code 3(Y)

Section 15: Regulatory Information

These products are hazardous goods approved by the National Environmental Authority (Singapore) under the Group Standard for Additives, Intermediates, Process Chemicals, Raw Materials.

LUZON:

REGIONAL OFFICE 1st Avenue, Sta. Maria Industrial Subd. Bagumbayan, Taguig City Tel.#: (02) 506-8519 ; 837-0710

Marine Pollutant

VISAYAS:

HEADQUARTERS

ZF SEA Olympus Building, AC Cortes Ave. Trunkline #: (032) 421-7777 Tel.#: (032) 346-7137 ; 421-7800 to 06 421-7817 to 18 ; 421-7823 Fax #: (032) 421-7789 ; 346-1817

MINDANAO:

REGIONAL OFFICE Unit A16 J.King Warehouse Complex Km.3 Maa Road, Davao City 8000 Telefax #: (082) 244-1206; 302-2711





































SEA Olympus Marketing, Inc. reserves the right to change the information given herein without prior notice. We believe this information to be reliable, but do not guarantee its applicability to the user's process or assume liability for occurrence arising out of its use. The user, by accepting products described herein agrees to be responsible for thoroughly testing any application before committing to production. ©20

LUZON:

REGIONAL OFFICE 1st Avenue, Sta. Maria Industrial Subd. Bagumbayan, Taguig City Tel.#: (02) 506-8519 ; 837-0710 837-0708

VISAYAS:

HEADQUARTERS HEADQUARTERS
CEBU
2F SEA Olympus Building, AC Cortes Ave.
Trunkline #: (032) 421-7777
Tel.#: (032) 346-7137; 421-7800 to 06
421-7817 to 18; 421-7823
Fax #: (032) 421-7789; 346-1817

MINDANAO:

REGIONAL OFFICE DAVAO Unit A16 J.King Warehouse Complex Km.3 Maa Road, Davao City 8000 Telefax #: (082) 244-1206; 302-2711





TECHNICAL DATA SHEET

POLYKLEAR R99-S205-03 PREMIX THIXOTROPED (BQTN-O)

A. DESCRIPTION

POLYKLEAR R99-S205-03 RESIN GP PREMIX THIXOTROPED is thixotropic, quick curing unsaturated polyester resin of orthophthalic grade for general purpose laminating purposes. It is waxed and pre-accelerated, suitable for both hand lay-up and gun spray-up. Other variants of this general-purpose resin are also available. A non-waxed type is needed for laminating between top and bottom.

B. APPLICATIONS

This resin is used for making a variety of glass fiber reinforced plastic products such as boats and canoes, bus shelters, telephone booths, stadium seat, bath tubs, water and storage tanks, cooling towers, plant and flower pots, bath unit, models, containers, dustbins, safety helmets, water and oil pipes, ash trays, septic tanks, car body, sporting equipment, concrete framings, chairs and tables, and other household articles. Glass fiber reinforced laminates made with this resin possess excellent mechanical strength and have good rigidity and outstanding durability.

C. SPECIFICATIONS

Liquid PLK R99-S203 polyester has the following characteristics:

Appearance

Viscosity at 30°C (Brookfield LVT, spindle 3, 60rpm)

Gel Time at 30°C FILE RG LASS - II 10 – 18 minutes

Peak Exothermic Temperature 135°C – 155°C Stability in the Dark below 25°C 6 months

Acid Value 20 – 24mgKoH/g (Styrenated resin)

Pink

4 - 6 ps

Above gelation characteristics determined using 1% v/w of MEKP catalyst (Butanox M-50) on 40g of resin.

D. USAGE

PLK R99-S203 performs best when it is completely cured. To do so, a proper combination of catalyst and accelerator must be used at room temperature for a sufficient period of time.

LUZON:

REGIONAL OFFICE TAGUIG 1st Avenue, Sta. Maria Industrial Subd, Bagumbayan, Taguig City Tel.#: (02) 506-8519; 837-0710 837-0708

VISAYAS:

HEADQUARTERS
CEBU
2F SEA Olympus Building, AC Cortes Ave.
Trunkline #: (032) 421-7777
Tel.#: (032) 346-7137; 421-7800 to 06
421-7817 to 18; 421-7823
Fax #: (032) 421-7789; 346-1817

MINDANAO:

REGIONAL OFFICE DAVAO Unit A16 J.King Warehouse Complex Km.3 Maa Road, Davao City 8000 Telefax #: (082) 244-1206; 302-2711





Generally, 1 percent of catalyst (BUTONOX M-50 MEKP) together with 0.5 percent of accelerator (6% cobalt content) is used.

Adjustments for shorter or longer gel time can be achieved by ranging the quantities of catalyst and/or accelerator used. As a rule, however, the amount of catalyst used should not be more than 2% or less than 0.5% while that of accelerator should range between 0.4% and 1%. Be sure to measure accurately.

Ensure that the accelerator must be completely mixed into the resin before catalyst is added in order to avoid a direct blending which due to a violent reaction may result in an **EXPLOSION.**

Since the viscosity increased as the storage period of resin lengthens, Styrene Monomer can be added to lower it to a desired level.

However owing to difficulties in presenting information applicable to all situations, no warranty is expressed or implied and users are recommended to carry out their own tests to determine the applicability of the above information and the suitability of PLK resin for their particular requirements.

E. STORAGE

PLK polyester resin will remain stable if stored in the dark and at temperatures below 25 °C. Their stability however deteriorates markedly at higher temperatures, especially when they are directly exposed to sunlight. Hence they should be kept in a cool, dark place. It is advisable to finish it within three months.

F. PACKING

PLK polyester resin is packed in liters, gallons, tins, pails and steel drums of standard size, containing 950g, 3.65kg, 15kg, 20kg, 220 kg net weight, respectively

SEA Olympus Marketing, Inc. reserves the right to change the information given herein without prior notice. We believe this information to be reliable, but do not guarantee its applicability to the user's process or assume liability for occurrence arising out of its use. The user, by accepting products described herein agrees to be responsible for thoroughly testing any application before committing to production. ©20

LUZON:

REGIONAL OFFICE 1st Avenue, Sta. Maria Industrial Subd. Bagumbayan, Taguig City Tel.#: (02) 506-8519 ; 837-0710

VISAYAS:

HEADQUARTERS ZF SEA Olympus Building, AC Cortes Ave. Trunkline #: (032) 421-7777 Tel.#: (032) 346-7137 ; 421-7800 to 06 421-7817 to 18 ; 421-7823 Fax #: (032) 421-7789 ; 346-1817

MINDANAO:

REGIONAL OFFICE Unit A16 J.King Warehouse Complex Km.3 Maa Road, Davao City 8000 Telefax #: (082) 244-1206; 302-2711